

Product Information

Construction:	Biaxial Orientation polypropylene
Main Application:	Single sided or double sided application; Easy application; Protects against abrasion, moisture and constant surface contact.
Benefits:	Non-solvent based adhesive protects the print from colour changing. No bubble, wrinkle or delamination.
Storage Conditions:	Stored up to 25°C, 50% relative humidity, in original packing of the box.
Adhesive:	Thermal Activated EVA Adhesive
Finishes:	Gloss & Matt
Core:	2" (58mm) or 3"(76mm)

Lamination Curing Time: Once the lamination is completed, it is recommended to lay the laminated print flat for 24 hours to allow the proper adhesive curing time prior to trimming.

Thickness

	Gloss	Matt
Base Thickness:	12 ± microns	15 ± microns
Adhesive Thickness:	13 ± microns	12 ± microns
Total Thickness:	25 ± microns	27 ± microns

Standard Stock Sizes

Codes		Standard size	Core	Adhesive
Gloss	Matt			
BF42	BF46	320mm x 3000m	76mm	Thermal Activated EVA
	BF36	445mm x 3000m	76mm	Thermal Activated EVA

* Outdoor life will vary depending on installation technique, location and relative position to the sun.

V1.2

PLEASE NOTE – All information, recommendations and suggestions contained herein, without limitation, stated values (collectively the "information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The information does not constitute a warranty or guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own tests. The seller shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the information.

ALC

www.alclaminating.com

Australian Laminating Company

Pty Ltd

76 North View Drive
Sunshine West Vic 3020

P: +61 (0)3 9312 7400
F: +61 (0)3 9312 7455
sales@alclaminating.com